

International standards	AWS A5.13	ECoCr-A
	DIN 8555	W / SG 20--40-CTZ

Approvals ---

Characteristics CARBO TS 6 is a bare rod for TIG- welding. The deposit is a cobalt base alloy of austenitic-ledeburitic structure with embedded CrW carbides. The weld metal is highly resistant to corrosion, impact, abrasive wear as well as thermal shocks and heavy mechanical impact. Good aptitude for polishing and machining.

Welding instructions Working temperature should be kept between 400° and 600°C, depending on base material and type of construction. Slow cooling, if necessary oven cooling, is recommended for low alloyed and austenitic steels. Subsequent heat treatment (stress relief at 700°C approx.) is not necessary, except on large structures.

Operating temperature From room temperature up to + 600° C

Typical applications Due to its above-mentioned characteristics CARBO SK 6 is particularly recommended for use on steam valves, hot shear blades, hot pressing dies, pumps for high-temperature liquids, etc.

Mechanical properties of all-weld metal (typical values)	At Rt. HRc	+ 300°C HRc	+ 600°C HRc	Melting- range °C	Density g/cm³
	ca. 42	ca. 35	ca. 29	1280-1390	8,3

Weld metal analysis (typical, wt. %)	C	Si	Mn	Cr	W	Fe	Co	Others
	1	0,9	1	28	4,5	3	Base	< 3

Current = -

Welding positions PA, PB, PC , PD, PE, PF

Gas types EN 439 I 1: Argon

Flux-cored wire equivalent CARBO F- S 6

Dia./Length	Pcs./packet	Pcs./carton	kg/1000	kg/packet	kg/carton
2,5 x 350	333	1333	15,0	5,0	20,0
3,2 x 350	200	800	25,0	5,0	20,0
4,0 x 350	147	588	34,0	5,0	20,0
5,0 x 350	91	363	78,7	5,0	20,0